

(11)



Europäisches Patentamt

European Patent Office

Office européen des brevets

(11) Publication number:

**0 154 831
B1**

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification: 19.12.90

(21) Application number: 85101638.6

(22) Date of filing: 14.02.85

(51) Int. Cl.⁵: C 08 F 2/24, C 08 G 85/00,
C 08 J 3/16, C 08 J 3/11,
A 61 K 7/00

(64) Rod-shaped polymer latex, rod-shaped polymer fine power and dispersion comprising the fine powder dispersed in non-aqueous medium.

(30) Priority: 28.02.84 JP 36380/84
08.06.84 JP 117511/84

(43) Date of publication of application:
18.09.85 Bulletin 85/38

(45) Publication of the grant of the patent:
19.12.90 Bulletin 90/51

(64) Designated Contracting States:
AT CH DE FR GB LI

(56) References cited:
EP-A-0 008 809
FR-A-2 132 903
US-A-3 431 242

(70) Proprietor: Kao Corporation
14-10, Nihonbashi Kayabacho 1-chome
Chuo-Ku Tokyo 103 (JP)

(72) Inventor: Tsujii, Kaoru
1022-88, Himuro-cho
Utsunomiya-shi Tochigi-ken (JP)
Inventor: Yoshimatsu, Akira
4254-14, Hiraide-cho
Utsunomiya-shi Tochigi-ken (JP)

(74) Representative: Wächtershäuser, Günter, Dr.
Tal 29
D-8000 München 2 (DE)

EP 0 154 831 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European patent convention).

Courier Press, Leamington Spa, England.

Description

i) Field of the Invention:

This invention relates to rod-shaped polymer latices comprising latex particles having a novel rod shape, rod-shaped polymer fine powders, and dispersions comprising the fine powder in non-aqueous media.

ii) Description of the Prior Art:

Polymer latices or emulsions have been widely utilized as binders for paints, adhesives, paper coatings, immunodiagnostics, sizes for clothes. These latices are, in most cases, produced by emulsion polymerization and comprise particles which are spherical in shape. Recently, there has been proposed a method of preparing a polymer latex other than the emulsion polymerization in which a polymer latex called soap-free emulsion is prepared without use of any surface active agents. In this case, the particles are nothing but spheres. Thus, the shape of the particles currently utilized as polymer latices is spherical in all cases. On the other hand, attempts have been recently made to change the shape of latex particles. In fact, there have been proposed several odd-shaped latices. These particles can be broadly classified according to the shape thereof as follows.

(1) Core-shell type particles in which polymer particles have different components of the core and shell (Japanese Laid-open Patent Application No. 55-55414).

(2) Confetti particles in which polymer particles have irregularities on the surfaces thereof (Collection of Polymer Theses, Vol. 36 (1979)).

(3) Localized particles in which different types of polymers suffer phase separation in a latex (Kagaku Giken Report Vol. 35, 1980)).

In all the cases, however, spherical latex particles are provided as nuclei and are covered with arbitrary polymers by seed polymerization. Accordingly, latex particles are considered to be spherical particles of latices which are somewhat varied or modified in shape. According to the conventional polymerization methods, there could not be obtained latices comprising particles which are not spherical in shape but are so shaped as to enhance the function thereof.

From EP-A-8 809, fibrils of crosslinked polyester resin having a vesiculated structure are known. The fibrils are said to be useful as fillers for paints and viscosity modifiers for liquids.

There is a high demand for techniques of imparting higher performance to latices by changing the shape of latices particles. For instance, when polymer latices are used as paint binders, good thixotropic properties are required. With known spherical latices, however, such a requirement cannot be satisfied, so that it is usual to add other types of polymer compounds capable of imparting thixotropic properties to the latices. However, if it is possible to permit paints to develop thixotropic properties by changing the shape of latex particles, addition of the thixotropy-imparting polymers becomes unnecessary. With diagnostic latices, latex particles having a large surface area are required in order to increase an adsorption of antigen or antibody and enhance the sensitivity to immune reaction. As is well known, sphere is in such a shape that has the smallest specific surface area. In this sense, spherical latex particles are not suitable for use in latices for diagnosis.

Rod-shaped inorganic fine powders such as of kaolin, goethite, γ -iron oxide, wollastonite, light calcium carbonate, and the like have been widely utilized as pigments or thickeners for make-up cosmetics, paints, paper coatings and the like. However, these materials are all natural inorganic materials, so that their properties are substantially similar to one another and there has never been known any material which is substantially different in nature from other materials. With regard to surface properties, for example, these known materials are hydrophilic in nature. Accordingly, it is usual practice that if hydrophobicity is required as with loading pigments for make-up cosmetics, the pigment is inevitably treated to impart the hydrophobicity thereto. Moreover, the inorganic materials are great in specific gravity, so that when they are used as dispersions in non-aqueous media (e.g. oil paints), it is necessary to prevent the materials from setting. In addition, these natural products have the problem that a constant quality cannot be ensured. For instance, with wollastonite, their major axis distributes from 1 μ m to about 500 μ m. Moreover, because of the presence of impurities, these natural rod-shaped inorganic powders have to be purified through a number of steps, with various problems accompanied at the time of effective utilization of these natural fine powders.

SUMMARY OF THE INVENTION

Under these circumstances, the present inventors made intensive studies to obtain polymer latices comprising latex particles of a novel shape and rod-like or rod-shaped polymer fine powders which have more uniform sizes than natural inorganic powders and overcome the drawbacks of the natural inorganic powders. As a result, it was found that latex particles in polymer latices which were obtained by the solubilization polymerization method described hereinafter had a large surface area and had high thixotropic properties. When water and, if necessary, a surface active agent used were removed from the polymer latices, rod-shaped fine powder could readily be obtained. The fine powder could be dispersed in non-aqueous media to obtain dispersions. The present invention is accomplished on the basis of the above finding.

EP 0 154 831 B1

According to the present invention there is provided a process for producing a rod-shaped polymer fine powder having a major axis of from 0.1 to 100 μm and a minor axis of below 1/3 time the major axis as defined in claim 1.

A rod-shaped polymer latex which comprises latex particles having a major axis of from 0.1 to 100 μm and a minor axis of below 1/3 time the major axis, an aqueous dispersion of the particles at a concentration of not larger than 15 wt% having a thixotropy index, η_3/η_{30} , of not less than 1.5 in which η_3 and η_{30} , respectively, represent viscosities when measured by means of the Brookfield viscometer at 3 and 30 r.p.m. may be used in the process of the present invention.

Also, there is provided a dispersion comprising the fine powder dispersed in a non-aqueous medium.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is an electron microphotograph showing the structure of latex particles of the invention obtained using sodium hexadecenylsuccinate (degree of neutralization of 0.7); Fig. 2 is an electron photomicrograph showing the structure of latex particles of the invention obtained using N,N-dimethyl-N-(carboxymethyl)-octadecylammonium inner salt (molar fraction of 0.5) and sodium octadecylsulfate (molar fraction of 0.5); Fig. 3 is an electron microphotograph showing the structure of latex particles of the invention obtained using octadecyltrimethylammonium halogenated benzoate; Fig. 4 is a scanning electron microphotograph showing the structure of latex particles obtained using ethylene oxide adduct of didodecylglycerine ether (moles of added ethylene oxide: 20); and Fig. 5 is a microphotograph showing the structure of spherical latex particles obtained in Comparative Example 1.

DETAILED DESCRIPTION OF THE INVENTION AND PREFERRED EMBODIMENTS


The rod-shaped polymer latices used in the process of the invention may be obtained by polymerizing various polymerizable monomers indicated thereafter and have such a shape that a minor axis of the latex particles is below 1/3 time the major axis. In general, the major axis is not larger than 100 μm . Preferably the major axis is in the range of from 0.1 to 15 μm and the minor axis is in the range of from 0.01 to 0.3 μm .

According to the present invention, the rod-shaped polymer latices are prepared by solubilizing a polymerizable monomer in rod-shaped micelles, and polymerizing the monomer while keeping the rod-shaped micelle structure.

The solution comprising the rod-shaped micelles may be defined in terms of spinnability of liquid, flow-induced optical anisotropy, Weissenberg effect of the like, but is defined most accurately in terms of dynamic elastic modulus. Examples of such solution are aqueous surface active agent solutions whose dynamic elastic modulus is not less than 0.001 N/m² (0.01 dyne/cm²) in a frequency range of from 0.05 to 1.0 Herz. Although the dynamic elastic modulus of the aqueous surface active agent solution may be over 0.001 N/m² (0.01 dyne/cm²), inclusive, the modulus is preferably in the range of from 0.05 to 1 N/m² (0.5 to 10 dyne/cm²). If the dynamic elastic modulus is lower than 0.001 N/m² (0.01 dyne/cm²), the rod-shaped micelles are broken by the addition of monomers. On the other hand, when the modulus is higher than 1 N/m² (10 dyne/cm²), the rod-shaped polymer latex can be formed but agitation at the time of the production becomes difficult.


Surface active agents which satisfy the above requirements include those agents indicated in (a) through (f) below.

(a) Compounds of the following general formula



in which R represents a hydrocarbon group having from 6 to 24 carbon atoms, and X and Y independently represent a hydrogen atom, an alkali metal, ammonium, an alkanolamine having from 2 to 3 carbon atoms, or a basic amino acid.


(b) Compounds of the following general formula



in which R₁ represents a hydrocarbon group having from 8 to 24 carbon atoms, R₂, R₃ and R₄ independently represent a hydrocarbon group or a hydroxyhydrocarbon group having from 1 to 3 carbon atoms, or a benzyl group, and Z[⊖] represents a counter anion.


EP 0 154 831 B1

(c) Compounds of the following general formula



in which R_5 and R_6 independently represent a hydrocarbon group having from 6 to 24 carbon atoms, n is an integer of from 1 to 50, and A represents one or more of hydrocarbon groups each having from 2 to 4 carbon atoms.

(d) Surface active compositions comprising the following two ingredients (A) and (B) in a ratio by weight of 100:20 to 30:100.




in which R represents a hydrocarbon group having from 6 to 24 carbon atoms, n_1 represents an integer of from 1 to 20, A represents a hydrocarbon group having from 2 to 4 carbon atoms, X_1 represents ammonium, an alkali metal, an alkaline earth metal, an alkanolamine having from 2 to 3 carbon atoms, or a basic amino acid.



in which R_7 represents a hydrocarbon group having from 6 to 24 carbon atoms, R_8 , R_9 , and R_{10} independently represent a hydrocarbon group or hydroxyhydrocarbon group, each having from 1 to 3 carbon atoms, or a benzyl group, n_2 is an integer of from 1 to 10, and Z^- represents a counter anion.


EP 0 154 831 B1

(e) Compounds of the following general formula



in which R_7 , R_8 and R_9 have, respectively, the same meanings as defined before.

(f) Compounds of the following general formula



in which R_{10} represents a hydrocarbon group having from 6 to 24 carbon atoms, R_{11} represents a hydrocarbon group having from 1 to 24 carbon atoms, R_{12} represents a hydrocarbon group having from 1 to 4 carbon atoms, A and n have, respectively, the same meanings as defined before.

Preferable examples of these surface active agents include: partially neutralized products of alkyl or alkenylsuccinic acid whose hydrocarbon moiety has from 6 to 24 carbon atoms such as, for example, dodecylsuccinic acid, octadecylsuccinic acid, dodecenylsuccinic acid, octadecenylsuccinic acid and the like; mixtures of N,N-dimethyl-N-(carboxymethyl)alkylammonium inner salts whose hydrocarbon moiety has from 6 to 24 carbon atoms and sodium alkylsulfates whose alkyl moiety having from 6 to 24 carbon atoms; mixtures of N,N-dimethyl-N-(3-sulfopropyl)alkylammonium inner salts whose alkyl moiety has from 6 to 24 carbon atoms and sodium alkylsulfates having from 6 to 24 carbon atoms; alkyltrimethylammonium halogenated benzoates or salicylates whose hydrocarbon moiety has from 6 to 24 carbon atoms; ethylene oxide adducts of dialkyl glycerine ethers whose hydrocarbon moiety has from 6 to 24 carbon atoms; and ethylene oxide adducts of Guerbet alcohols.

In the practice of the invention, polymerizable monomers used may be any monomers which are used in ordinary polymerization reactions such as, for example, radical polymerization reactions, polycondensation reactions, and polyaddition reactions.

The polymerizable monomers used in the present invention are described below with regard to the radical polymerization, polycondensation and polyaddition reactions along with the preparation of rod-shaped polymer latices.

(i) Radical Polymerization

Useful polymerizable monomers are any known monomers which are ordinarily used for emulsion polymerization and include, for example, ethylenically unsaturated monomers such as ethylene, propylene, isobutene, butene-1 and the like; aromatic vinyl monomers such as styrene, α -methylstyrene, vinyltoluene, halogenated styrene, divinylbenzene and the like; acrylic esters whose alkyl group has from 1 to 20 carbon atoms such as ethyl acrylate, butyl acrylate, 2-ethylhexyl acrylate and the like; methacrylic esters whose alkyl group has from 1 to 20 carbon atoms such as methyl methacrylate, butyl methacrylate, lauryl methacrylate and the like; vinyl esters such as vinyl acetate, vinyl propionate and the like; vinyl ethers having from 1 to 20 carbon atoms such as ethyl vinyl ether, butyl vinyl ether and the like; vinyl ketones having from 1 to 20 carbon atoms in an alkyl group such as methyl vinyl ketone, ethyl vinyl ketone and the like; vinyl cyanide monomers such as acrylonitrile, methacrylonitrile and the like; vinyl halides such as vinyl chloride, vinyl bromide, vinylidene chloride, vinylidene bromide and the like; and aliphatic conjugated dienes such as vinylidene halides, 1,3-butadiene, 2-methyl-1,3-butadiene and the like. These monomers may be used singly or in combination of two or more. In addition, the above monomers may be copolymerized with maleic anhydride, water-soluble monomers, styrene sulfonic acid or sulfonates, vinyl naphthalenesulfonic acid or naphthalenesulfonates and acrylates.

The most preferable procedure for preparing rod-shaped polymer latices comprises the steps of preparing an aqueous solution having viscoelasticity by charging a surface active agent into a reactor in which water is placed, adding a polymerizable monomer and, if necessary, a radical polymerization initiator under heating and agitating conditions while keeping the viscoelastic property of the solution, thereby starting the polymerization, and further adding the monomer gradually under such conditions that the dynamic elastic modulus of the aqueous solution of the surface active agent is within the range defined before.

The radical polymerization initiators include, for example, persulfates such as potassium persulfate, sodium persulfate, ammonium persulfate and the like; azo compounds such as mineral acid salts of 2,2'-azobis(2-amidinopropane), azobiscyanovaleiranic acid and alkali metal and ammonium salts thereof; and peroxide compounds such as benzoylperoxide, laurylperoxide and the like; Redox initiators such as tartaric acid-hydrogen peroxide, rongalit-peroxides, ascorbic acid-peroxides and the like. Of these, salts of 2,2'-

EP 0 154 831 B1

azobis(2-amidinopropane) and mineral acids are preferred when cationic surface active agents are used in the polymerization system, and persulfates are preferred in other polymerization systems. The amount of radical polymerization initiator is in the range of 0.1 to 5 parts by weight (hereinafter referred to simply as parts), preferably from 0.1 to 3 parts, per 100 parts of the monomer used.

The reaction temperature should be a maximum temperature such that a dynamic elastic modulus can be maintained in a reaction solution and is preferably in the range of from 50 to 90°C. The time required for the polymerization depends on the type, composition and concentration of monomer, the concentration of radical polymerization initiator, and the polymerization temperature and is preferably within a range of from 5 to 50 hours.

(ii) Polycondensation

Polycondensation monomers useful for the purpose of the invention may be any known monomers which are used for interfacial polycondensation or low temperature polycondensation. Of these, monomers capable of producing polyamides and polyesters are preferred. For instance, acid components used to prepare polyamides include alkylenedicarboxylic acids comprising hydrocarbon moieties having from 1 to 24 carbon atoms, dimer acids, phthalic acids such as terephthalic acid, isophthalic acid and the like, aromatic polyvalent carboxylic acids, acid chlorides or acid anhydrides corresponding to cyclic aliphatic polyvalent carboxylic acid, thio esters of dicarboxylic acids, and the like. Diamine components include, for example, aliphatic polyvalent amines comprising hydrocarbon moieties having from 1 to 24 carbon atoms, such as alkylenediamines, alkylenetriamines and the like, aromatic polyvalent amines such as phenylenediamine, 4,4'-diaminophenyl ether and the like, polyvalent amines having heterocyclic rings, and the like.

Alcohol components used to prepare polyesters include, for example, ethylene glycol condensates having hydrocarbon moieties having from 1 to 24 carbon atoms, such as alkylene diols, bis- β -hydroxyethyl terephthalate and the like, aromatic polyvalent alcohols such as hydroquinone, bisphenol A and the like, polyols such as glycerine derivatives, and the like. The acid components are those compounds as described above with respect to polyamides. As a matter of course, other types of monomers may also be used in the practice of the invention. The monomers indicated above may be used singly or in combination.

For the preparation of rod-shaped polymer latices, a surface active agent is added to a reactor in which water is placed and agitated to solubilize an acid component therein, followed by adding an aqueous solution of a diamine or alcohol. Alternatively, separate solutions of both components in organic solvents may be, respectively, added to and solubilized in aqueous solutions of surface active agents, and then combined together. Where a monomer used is solid, it is preferable to dissolve the solid monomer in an organic solvent and solubilize the monomer in rod-shaped micelles along with the solvent for subsequent polycondensation. The solvents used for these purposes should conveniently be insoluble in water and, preferably, benzene, toluene and xylene are used. The reaction temperature is a temperature such that a dynamic elastic modulus can be maintained in a reaction solution and is preferred to be within a range of from -10 to 50°C. The reaction time may vary depending on the type, composition and concentration of monomer and the reaction temperature and is preferably in the range of from 2 to 60 minutes.

(iii) Polyaddition

The addition-polymerizable monomers used for the polyaddition reaction may be any known monomers used for ordinary polyaddition reactions. Preferable monomers are those monomers capable of producing polyurethanes, polyurea resins, and epoxy resins.

Alcohol components used to prepare polyurethanes are compounds which have at least two hydroxyl groups in one molecule thereof. Specific examples of the alcohols include ethylene glycol, propylene glycol, butylene glycol, hexanediol, neopentyl glycol, polyethylene glycol, polypropylene glycol, polyoxytetramethylene glycol, glycerine, trimethylol propane, polyesters having two or more hydroxyl groups at ends thereof, and the like. The isocyanate components should have at least two isocyanate groups in one molecule thereof and specific examples of such isocyanates include tolylene diisocyanate, xylylene diisocyanate, hexamethylene diisocyanate, 4,4'-diphenylmethane diisocyanate, triphenylmethane triisocyanate, trimethylolpropane triisocyanate, and polyesters, polyethers and polyurethanes having two or more isocyanate groups at ends thereof.

The isocyanate components used to prepare polyurea resins may be such compounds as indicated above. The amine components should have at least two amino groups in one molecule thereof and specific examples of the amines include hexamethylenediamine, dodecylamine, phenylenediamine, diamino-diphenyl ether, piperidine and the like.

The epoxy components used to prepare epoxy resins should have at least two epoxy groups in one molecule thereof. Specific examples of the epoxy components include glycidyl ether compounds of bisphenol A, glycidyl ester compounds of dimer acids, and compounds obtained by oxidation of olefins. The amine components may be those amine compounds indicated above with respect to the polyurea. Hardening agents may be any known agents including, for example, tertiary amines, boron trifluoride-amine complexes, imidazoles, and other substances having functional groups capable of polyaddition reaction with epoxy groups such as amines, polyamines, carboxylic anhydrides, polysulfides, dicyandiamides, and diisocyanates.

EP 0 154 831 B1

The rod-shaped polymer latices are prepared as follows. In order to produce polyurethane and polyurea resins, surface active agents are added to a reactor in which water is placed and agitated to solubilize an isocyanate component, followed by adding an aqueous solution of a diol or diamine. Alternatively, both components may be separately dissolved in organic solvents and the resulting solutions are solubilized in separate aqueous surface active agent solutions, followed by combining both solutions together. For the preparation of epoxy resins, a solution of a prepolymer or terminal epoxy compound and a hardening agent in solvents is gradually dropped into a hot aqueous solution of a surface active agent.

Where the monomers used above are solid or highly viscous liquid, it is preferred that they are dissolved in organic solvents and are solubilized in rod-shaped micelles along with the solvent, followed by polyaddition reaction. The organic solvents should be inert solvents which are insoluble in water and are incapable of reaction with other components. Preferable examples include benzene, toluene and xylene. The reaction temperature is a temperature such that a dynamic elastic modulus can be maintained in a reaction solution and is preferably in the range of from 20 to 70°C. The reaction time may vary depending on the type, composition and concentration of monomer and the reaction temperature, and is preferably in the range of from 1 to 50 hours.

It will be noted that phenolic resins which are polycondensates may be prepared similar to the above-described rod-shaped polymer latices of epoxy resins. For the preparation of the phenolic resin latices, phenol or phenolic derivatives such as cresol and formaldehyde are used. In addition, resol or novolac resins may be hardened by the use of acids or polyamines.

Rod-shaped polymer fine powders are prepared from the rod-shaped polymer latices by removing water and, if necessary, surface active agents from the latices.

Water and surface active agents can be removed from the latices by various techniques such as freeze-drying, centrifugal separation, precipitation with organic solvents miscible with water, precipitation by salting-out, and the like. The removal techniques should be determined depending on the use of the resulting powder. For instance, if surface active agents may be left in the powder, it is convenient to produce the fine powder by freeze-drying. On the other hand, if rod-shaped polymer fine powder is precipitated by addition of a solvent such as ethanol to the latex, surface active agents soluble in ethanol can be relatively easily removed. The powder form which the surface active agent has been removed is suitable as a powder for make-up cosmetics which are used in direct contact with the skin.

Non-aqueous media used to disperse the fine powder therein are selected depending on the type of final commercial product. Examples of such media include: monoalcohols, polyols and glycol ethers such as methanol, ethanol, glycerine, ethylene glycol and the like; nitriles such as acetonitrile, butyronitrile and the like; halogenated methanes and halogenated ethanes such as chloroform, bromoform and the like; ketones such as acetone, methyl ethyl ketone and the like; esters such as ethyl acetate, butyl acetate and the like; aromatic solvents such as benzene, toluene and the like; triglycerides such as castor oil, olive oil, rape oil and the like; and vaseline and paraffin.

[Effects of the Invention]

The rod-shaped polymer latex particles and fine powder thereof are substantially different in nature from odd-shaped latices in which polymer cores are covered with a different type of polymer, and have thus a specific functional form obtained by the solubilization polymerization as will not be experienced up to now. The rod-shaped polymer latices and powders can be applied to a wide variety of fields utilizing the structural anisotropy. For instance, they are useful as thickeners and paints in view of the high thixotropy of a dispersion. Because of the structural anisotropy of rod-shaped latices, the latices are useful as substrates for cosmetics such as lotions, creams, powders and the like. Moreover, the latices whose particles are larger in specific surface area than known spherical latex particles are likely to adsorb proteins and can be used as a carrier for immunodiagnostics.

The dispersions of the rod-shaped polymer fine powders in non-aqueous media are relatively unlikely to coagulate and, when applied to the skin, they are smooth to the touch and are particularly useful as substrates for make-up cosmetics. The dispersion may further comprise cosmetic ingredients ordinarily used for the cosmetic purposes.

The present invention is described in more detail by way of examples and comparative examples, in which parts are by weight.

Example 1

Into a 300 ml separable glass four-necked flask equipped with an agitator were charged distilled water and each of various surface active agents indicated in Table 1 to prepare a viscoelastic solution, followed by complete substitution with nitrogen and heating to 60°C to 75°C while agitating. Thereafter, 20 parts of styrene and an aqueous solution of 0.5 part of ammonium persulfate serving as a radical initiator in 10 parts of distilled water were dropped in 2 hours while keeping the viscoelasticity. The viscoelasticity could be readily recognized because when the agitation was stopped, the solution was reversely turned or swung. The polymerization was carried out at 60 to 75°C for further 6 hours.

One hundred parts of the resulting latex solution was charged into 200 parts of ethanol to allow precipitation of a gel-like latex. The solution was placed in a centrifuge tube and subjected to centrifugal separation at 1000 r.p.m. for 15 minutes. The resulting latex cake was again dispersed in ethanol, followed

EP 0 154 831 B1

by repeating the centrifugal separation under the same conditions as used above. The thus obtained latex was dried to obtain a rod-shaped polystyrene powder. Scanning electron microphotographs exhibiting the particle structure of the rod-shaped polystyrene are shown in Figs. 1 through 4. As will be clearly seen from the microphotographs, the latex has a rod-shaped form. The relation between dynamic elastic modulus of aqueous solutions of various surface active agents and shape of the resulting latices is shown in Table 1. The dynamic elastic modulus was determined as follows: a sample solution was placed in a double cylinder closed at one end thereof; and sine wave vibrations were applied to the outer cylinder whereupon a phase difference and an amplitude ratio of the sine wave vibrations transmitted to the inner cylinder were measured by a rheometer (Thixotrometer, by Iwamoto Seisakusho K.K.).

TABLE 1

Dynamic Elastic Modulus of Surface Active Agent Aqueous Solutions
and Shape of Produced Latices

Surface Active Agent	Parts	Dynamic Elastic ^{a)} Modulus N/m ² (dyne/cm ²)	Shape
sodium hexadecenylsuccinate	4	0.12 (1.20)	rod
N,N-dimethyl-N-(carboxymethyl) octadecylammonium inner salt (0.5) ^{a)} + sodium octadecylsulfate (0.5) ^{a)}	4	0.022 (0.22)	rod
N,N-dimethyl-N-(3-sulfopropyl) octadecylammonium inner salt (0.3) ^{a)} + sodium octadecylsulfate (0.7) ^{a)}	4	0.011 (0.11)	rod
octadecyltrimethylammonium halogenated benzoate	2	0.2 (2.00)	rod
didodecylglycerine ether ethylene oxide adduct (the number of moles of added ethylene oxide: 20 moles)	8	0.024 (0.24)	rod
sodium dodecylsulfate	0.2	0 (0)	sphere

^{a)} Mixing molar ratio.

^{b)} Frequency is 0.08 Hz.

Example 2

Example 1 was repeated except that a solution of a surface active agent consisting of N,N-dimethyl-N-(carboxymethyl)octadecylammonium inner salt and sodium octadecylsulfate was used to polymerize styrene. The relation between molar fraction and shape of latex particles is shown in Table 2.

EP 0 154 831 B1

TABLE 2

Influences of Molar Fraction f N,N-dimethyl-N-(carboxymethyl)octadecylammonium Inner Salt (A)

	Molar Fraction f	Dynamic Elastic Modulus N/m ² (dyne/cm ²)	Shape
5			
10	0.2	0 (0)	sphere
	0.3	<0.001 (<0.01)	sphere
15	0.4	0.017 (0.17)	rod
	0.5	0.022 (0.22)	rod
	0.6	0.018 (0.18)	rod
20	0.7	0.014 (0.14)	rod
	0.8	0 (0)	sphere
25	0.9	0 (0)	sphere
$f = [A]/([A] + [\text{sodium octadecylsulfate}])$ The dynamic elastic modulus is a value measured at a frequency of 0.08 Hz.			

Example 3

Example 1 was repeated using solutions of surface active agents including ethylene oxide adduct of α,α' -didodecylglycerine ether, octadecyltrimethylammonium p-chlorobenzoate, and a mixture of N,N-dimethyl-N-(carboxymethyl)octadecylammonium inner salt and sodium octadecylsulfate. The relation between polymerization temperature and shape of latex particles is shown in Table 3 below.

TABLE 3

Influences of Polymerization Temperature

40	A								B		C	
45	Tempera- ture °C	Dynamic Elastic (a) N/m ² (dyne/cm ²)		Shape	Dynamic Elastic (b) N/m ² (dyne/cm ²)		Shape	Dynamic Elastic (c) N/m ² (dyne/cm ²)		Shape		
50	40	0.025 (0.25)		rod	0	(0)	sphere	0.03	(0.3)	rod		
	50	0.025 (0.25)		rod	0	(0)	sphere	0.025 (0.25)		rod		
	60	0.022 (0.22)		rod	0.005 (0.05)		rod	0.23 (2.30)		rod		
55	70	<0.01 (<0.01)		sphere	0.012 (0.12)		rod	0.005 (0.05)		rod		
	80	0	(0)	sphere	0	(0)	sphere	0	(0)	sphere		
	90	0	(0)	sphere	0	(0)	sphere	0	(0)	sphere		

A: N,N-dimethyl-N-(carboxymethyl)octadecylammonium inner salt (mixing ratio: 0.5) + sodium octadecylsulfate (mixing ratio: 0.5).

B: ethylene oxide adduct of α,α' -didodecylglycerine ether (moles of added ethylene oxide: 20),

C: octadecyltrimethylammonium halogenated benzoate. Frequencies: (a) 0.08 Hz, (b) 0.08 Hz, (c) 0.5 Hz.

EP 0 154 831 B1

Example 4

The general procedure of Example 1 was repeated using sodium hexadecylsuccinate (degree of neutralization: 0.7) and a monomer composition comprising 30 parts of styrene and 0.15 part of sodium styrenesulfonate. To the resulting solution was added triethanolamine, followed by heating and charging into ethanol as it is to give a coagulum. The coagulum was washed with hot ethanol several times and was then charged into distilled water while containing ethanol. After removal of the ethanol by distillation, there was obtained a dispersion comprising 14.5% of the latex. The viscosity of the rod-shaped latex was measured by means of the Brookfield viscometer, revealing that a ratio of viscosities at 3 r.p.m. and 30 r.p.m. was such that $\eta_{30}/\eta_3 = 6.9$, thus the thixotropy index being very high.

Comparative Example 1

In the same manner as in Example 1, the aqueous initiator solution and styrene were mixed at one time and the polymerization was conducted in the solution having little viscoelasticity. The microphotograph of the resulting latex solution is shown in Fig. 5. The latex particles were spherical and had an average size of 0.7 μm . As will be appreciated from the above, the polymerization in the solution having little viscoelasticity is an ordinary emulsion polymerization, so that spherical latex particles are formed.

Comparative Example 2

Into a 500 ml separable glass flask equipped with an agitator were charged 150 parts of distilled water, 3 parts of sodium dodecylsulfate, 0.5 part of ammonium persulfate, 100 parts of styrene, and 0.5 part of sodium styrenesulfonic acid, followed by complete substitution with nitrogen and heating to 80°C under agitation. The polymerization was carried out for 8 hours to obtain a dispersion of spherical latex particles having an average size of 0.07 μm . The dispersion was dialyzed for 20 days using a cellophane dialysis membrane and distilled water, thereby removing the emulsifier. The resulting dispersion was diluted with distilled water to obtain a dispersion having a latex content of 14.5%. The viscosity of the dispersion was measured by the use of the B-type viscometer and was found to be 10 cps, showing no thixotropic properties.

Example 5

In the same manner as in Example 1 using hexadecylsuccinic acid as the surface active agent, styrene and sodium styrenesulfonate were polymerized. The results are shown in Table 4.

Examples 6, 7

The polymerization reaction was conducted in the same manner as in Example 1. Styrene and sodium styrenesulfonate were used as monomers in amounts indicated in Table 4 and 200 parts of 4% octadecyltrimethylammonium chlorinated benzoate was used as a surfactant. Thereby obtaining rod-shaped polystyrene/sodium sulfonate fine powder. The results are shown in Table 4.

Example 8

Twenty parts of styrene and 0.25 part of sodium styrenesulfonate were used as polymerizable monomers and polymerized in the same manner as in Example 1. Sodium hexadecylsuccinate was used as a surfactant, thereby obtaining a latex of polystyrene/sodium sulfonate. One hundred parts of the latex was immersed in an acetone-dry ice bath and frozen, followed by sucking with a vacuum pump for freeze-drying for 24 hours to obtain a rod-shaped polystyrene/sodium sulfonate fine powder. The fine powder had an average size and a degree of wetting with water as shown in Table 4.

EP 0 154 831 B1

TABLE 4

Properties of Rod-shaped Polymer Fine Powder

	Amount of Styrene (parts)	Amount of Sodium Styrene- sulfonate (parts)	Average Particle Size (μm)	Wetting ^{a)} to Water
Example				
1	20	0	4.0 ± 3	--
5	20	0.125	3.6 ± 2	-
6	20	0.25	10.6 ± 2	+
7	20	1.25	9.5 ± 2	++
8	20	0.25	3.8 ± 2	++
Comparative Example				
3	Kaolin		0.1 - 10	++
4	Wollastonite		5 - 500	++

^{a)} --: complete water repellency, -: slight water repellency, +: slight wetting, ++: complete wetting.
The values of the monomers are by parts.

Example 9 Rouge

(1) Titanium dioxide	2.0 (wt%)
(2) Red No. 204	2.5
(3) Red No. 220	0.5
(4) Yellow No. 4 Al lake	0.2
(5) Rod-shaped polystyrene fine powder (obtained in Example 5)	8.0
(6) Cetyl lactate	10.0
(7) Lanoline	5.0
(8) Castor oil	52.7
(9) Carunauba wax	2.0
(10) Candelilla wax	8.0
(11) Ceresin wax	4.0
(12) Beeswax	4.0
(13) Parfum	suitable amount
(14) Antioxidant	suitable amount

EP 0 154 831 B1

Ingredients (1) through (4) were added to part of the castor oil to obtain a uniform pigment composition. The other ingredients were heated and melted, followed by mixing with the pigment composition and uniformly dispersing in a homogenizer. After the dispersion, the dispersion was poured into a mold and cooled to obtain rouges which were able to apply uniformly and rarely suffered color drifting.

Claims

1. A process for producing a rod-shaped polymer fine powder having a major axis of from 0.1 to 100 μm and a minor axis of below $\frac{1}{2}$ time the major axis, characterized by solubilizing a polymerizable monomer in an aqueous surface active agent solution which has a dynamic elastic modulus of not lower than 0.001 N/m² (0.01 dyne/cm²) in a frequency range of from 0.05 Hz to 1.0 Hz, starting the polymerization in water, continuing the polymerization while adding monomer at such a rate that the dynamic elastic modulus of the aqueous surface active agent solution is within the above-defined range, and removing water and, optionally, the surface active agent from the resulting rod-shaped polymer latex, wherein said polymerizable monomer is solubilized in rod-shaped micelles, and polymerizing the monomer while keeping the rod-shaped micelle structure.
2. A process according to Claim 1, wherein the polymerizable monomer is a vinyl monomer or an acrylic monomer.
3. A dispersion comprising a rod-shaped polymer fine powder prepared in accordance with Claim 1 and dispersed in a non-aqueous medium.
4. The dispersion according to Claim 3, further comprising cosmetic materials.

Patentansprüche

1. Verfahren zur Herstellung eines stabförmigen Polymer-Feinpulvers mit einer Hauptachse von 0,1 bis 100 μm und einer kleineren Achse von weniger als dem $\frac{1}{2}$ -fachen der Hauptachse, dadurch gekennzeichnet, daß man ein polymerisierbares Monomeres in einer wässrigen Lösung eines oberflächenaktiven Mittels, die ein dynamisches Elastizitätsmodul von nicht unter 0,001 N/m² (0,01 dyne/cm²) in einem Frequenzbereich von 0,05 Hz bis 1,0 Hz aufweist, solubilisiert, die Polymerisation fortsetzt unter Zugabe von Monomerem mit einer derartigen Rate, daß das dynamische Elastizitätsmodul der wässrigen Lösung des oberflächenaktiven Mittels innerhalb des oben definierten Bereichs liegt und Wasser sowie gegebenenfalls das oberflächenaktive Mittel aus dem Stabförmigen Polymerlatex entfernt, wobei das polymerisierbare Monomere in stabförmigen Micellen solubilisiert wird, und das Monomere unter Einhaltung der stabförmigen Micel-Struktur polymerisiert wird.
2. Verfahren gemäß Anspruch 1, wobei das polymerisierbare Monomere ein Vinyl-Monomeres oder ein acrylisches Monomeres ist.
3. Dispersion umfassend ein stabförmiges Polymer-Feinpulver, hergestellt gemäß Anspruch 1 und dispergiert in einem nicht-wässrigen Medium.
4. Dispersion gemäß Anspruch 3, ferner umfassend kosmetische Materialien.

Revendications

1. Procédé de fabrication d'une poudre fine de polymère en forme de tige, ayant un grand axe de 0,1 à 100 μm et un petit axe inférieur au $\frac{1}{2}$ du grand axe, caractérisé par la solubilisation d'un monomère polymérisable dans une solution aqueuse d'agent tensio-actif, qui a un module d'élasticité dynamique non inférieur à 0,001 N/m² (0,01 dyne/cm²), dans une plage de fréquence allant de 0,05 Hz à 1,0 Hz, le démarrage de la polymérisation dans l'eau, la poursuite de la polymérisation tout en ajoutant du monomère à une vitesse telle que le module d'élasticité dynamique de la solution aqueuse d'agent tensio-actif se situe à l'intérieur de la plage définie ci-dessus, et l'élimination de l'eau et, facultativement, de l'agent tensio-actif du latex de polymère en forme de tige résultant, dans lequel ledit monomère polymérisable est solubilisé en micelles en forme de tige, la polymérisation du monomère étant effectuée tout en conservant la structure de micelles en forme de tige.
2. Procédé selon la revendication 1, dans lequel le monomère polymérisable est un monomère vinylique ou un monomère acrylique.
3. Dispersion comprenant une poudre fine de polymère en forme de tige, préparée conformément à la revendication 1 et dispersée dans un milieu non-aqueux.
4. Dispersion selon la revendication 3, comprenant en outre des matières cosmétiques.

FIG. 1



FIG. 2




FIG. 3





FIG.4



FIG.5



15